HI- GLOSS ENAMEL

Interior / Exterior Alkyd



White Base . CC9500 Deep Base . CC9501 Neutral Base. CC9502

SPECIFICATION DATA:

PERCENT SOLIDS:

BY WEIGHT: 66.8% BY VOLUME: 52.2%

PIGMENT: 30.3%

| Titanium Dioxide: Calcium Carbonate: | 80.0% 20.0% |
|---|----------------|
| | 100% |
| VEHICLE: 69.7% | 47.0% |
| Alkyd Resin: | |

| Additives: M i n e r a l Spirits: | 4.7% 48.3% |
|--------------------------------------|---------------|
| | |
| | 100% |

MIL FILM THICKNESS:

Wet: 3.8 Dry: 1.5 VOC < 350 g/l

COVERAGE:

Will cover up to 450 sq. ft per gallon

depending on surface conditions.

APPLICATION:

Brush, roller or airless spray. Apply only when air and surface temperature is above 50° F.

ColorCraft Paints, LLC

10160 NW South River Dr. | Medley, Florida 333178 954.899.8971 | sales@cocraft.net | colorcraftpaints.com

PRODUCT: ColorCraft - CC9500 GLOSS ENAMEL

FINISH: Gloss

TYPE: Alkyd

RECOMMENDED USES:

Interior / Exterior Primed metal and wood Primed stucco and masonry Concrete block Kitchen and baths Wood trim, cabinets and doors

CHARACTERISTICS:

Fine quality coating that dries to a beautiful gloss finish. Has excellent hiding, durability, scrubbability, and mildew resistance.

TINTING:

Can be tinted with universal colorants in White, Deep tint and Neutral bases.

PACKAGE SIZES:

Available in 1 gallon and quart size containers.

DRYING TIME:

At 77 F and 50% RH dries in 4 hours. Recoat after overnight drying.

THINNING:

Apply as supplied. If necessary, thin with up to $\frac{1}{2}$ pint of mineral spirits per gallon.

CLEAN UP Wash tools and equipment with mineral spirits.